

Farbton	Produkt	Farbe	CI	Pigment ca. %	Lichtbe- ständigkeit		Wetter- echtheit		Dichte (g/ml)	pH
					1/3	1/25	1/3	1/25		
	B1000	weiss	PW6	70%	8	8	5	5	2.10	10
	B1005	oxidrot	PR101	49%	8	8	5	5	1.66	10
	B1015	rot	PR254	42%	7 – 8	6 – 7	4	4	1.12	10
	B1025	oxidrot	PR101	49%	8	8	5	5	1.69	10
	B1030	orange	PO73	31%	7 – 8	7 – 8	4 – 5	4 – 5	1.05	10
	B1065	gelb	PY139	31%	8	8	4	3 – 4	1.15	10
	B1075	oxidgeib	PY42	44%	8	8	5	5	1.50	10
	B1095	gelb	PY138	48%	8	7 – 8	3 – 4	3	1.33	10
	B1105	gelb	PY184	61%	8	8	5	5	1.95	10
	B1180	grün	PG7	31%	8	8	5	4 – 5	1.25	10
	B1190	grün	PG17	60%	8	8	5	5	1.95	10
	B1205	türkis	PB28	50%	8	8	5	5	1.60	10
	B1245	blau	PB15:3	31%	8	8	5	4 – 5	1.16	10
	B1240	schwarz	PBk11	60%	8	8	5	5	1.80	10
	B1260	blau	PB15:6	32%	8	8	5	4 – 5	1.10	10
	B1275	blau	PB28	50%	8	8	5	5	1.63	10
	B1265	schwarz	PBk7	22%	8	8	5	4 – 5	1.13	10
	B1300	violett	PV23	13%	7 – 8	6 – 7	4	3	1.03	10
	B1340	rosa	PR122	19%	7 – 8	6 – 7	4 – 5	4 – 5	1.07	10

Auf Wunsch formulieren wir für Sie weitere Farbpasten.

